

MARK-170.2 BASECOAT

OVERVIEW

MARK-170.2 Parking Preservation Solutions is a concrete protection system that sets the industry standard for performance accountability by ensuring maximum service life for critical parking structure assets. Through the combination of advanced material technology, best-practices installation methods and performance accountability, the system results in improved protection outcomes and life-cycle cost savings for parking garage owners.

MARK-170.2 BASECOAT is a two-component, fast setting, rapid curing and solvent-free, and 100% solids polyurea. It is designed as a seamless, protective barrier against leakage and water intrusion. Optimum tensile strength and elongation properties allow expansion and contraction with inherent structural movement and freeze/thaw cycles, while bridging cracks.

FEATURES

- Self-leveling and fast curing, allowing for efficient installation
- Low temperature curing as low as 35°F (2°C)
- Impervious to water and deicing salts/liquids
- Excellent crack bridging characteristics
- Monolithic, durable membrane across wide temperature range

PRODUCT CHARACTERISTICS

- Color: off-white to light grey
- Mix Ratio by Volume: 6:1
- Shelf Life: 12 months

Applications

MARK-170.2 BASECOAT is a cold-applied, parking deck coating designed to provide long-term waterproofing for concrete slabs and protection for occupied areas from water damage. When used as part of a FLEXODECK installation, the membrane retains its integrity even in conditions where mild substrate movement causes hair-line cracks of up to 1/16th inch (1.5 mm).

Product Characteristics

	Part A	Part B
Appearance	Off-white Liquid	Amber Liquid
Viscosity at 77°F (24°C)	4000 cps	25 – 60 cps
Solids Content	100%	100%
Specific Gravity	1.15 g/mL	1.07 g/mL
Packaging	4.3 gal (16.3 L)	0.7 gal (2.6 L)
Wet Mills (mm)	23 - 40 mils (0.58-1.02 mm) or as needed to meet Performance Specification	
Coverage Rate ¹	40 - 70 sq.ft. per gallon (0.98-1.72 m ² per L) or as needed to meet Performance Specification	

1. Coverage may vary with the application technique used. Actual coverage rate and mil thickness dependant upon substrate porosity and surface profile.

Mixing and Handling

MARK-170.2 BASECOAT must be mixed in the following ratios:

	MARK-170.2 BASECOAT Polyisocyanate Resin	MARK-170.2 BASECOAT Hardener
Parts by Volume	100	16.6

Accurate proportioning and thorough mixing are essential to achieve full performance properties. Manually mix the resin and hardener components together for approximately 4 minutes while making sure to scrape the sides, bottom, and corners of the mixing container.

For large applications, it is a good practice to mix and use several small batches rather than one large batch.

The resin and hardeners used in this system will readily react with each other at ambient temperatures. This reaction is exothermic and, depending on the mass, can result in a significant temperature rise or fire. The utmost care must be taken to avoid inadvertent mixing of the system components. Refer to the Safety and Handling section for additional information.

Curing Characteristics & Mechanical Properties of Cured System^{1,2}

@ 77°F (25°C)

Initial Cure:	2 – 3 hours	
Pot Life:	15-20 minutes	ASTM C881
Time To Recoat:		
Minimum	2.5 hours	
Maximum	24 hours	
Tensile Strength	2,150 psi	ASTM D412
Elongation %	650%	ASTM D412
Crack Bridging Ability	Pass	ASTM C957
Adhesion	Concrete Failure > 500 psi	ASTM D4541/ACI 503

1. Curing time is temperature dependent. It is not humidity or thickness dependent.
2. If maximum recoat time is exceeded, Xylene wipe and reprime surface before proceeding with installation.

Safety and Handling

Olin POLY-CARB provides its customers with a product specific Material Safety Data Sheet (MSDS) or Safety Data Sheet (SDS) to cover potential health effects, safe handling, storage, use and disposal information. Olin strongly encourages its customers to review the MSDS or SDS on its products and other materials prior to their use.

The reaction between resins and hardeners is exothermic and, depending on the mass and starting temperature, can result in significant temperature rise, smoke generation or fire. The epoxy/amine chemical reaction is self sustaining and cannot be easily stopped. Therefore, the utmost care should be taken to avoid mixing excessive quantities of resin and hardeners and then leaving them unattended. In the event a large quantity of material is inadvertently mixed, it is advised that the mass of the mixed resin system be reduced and the surface area increased by pouring it into multiple containers or a large shallow pan in order to reduce the potential temperature rise.

Packaging, Storage and Shelf Life

MARK-170.2 BASECOAT Flexible Waterproofing Membrane is supplied in 6 gallon plastic containers and 1 gallon steel cans. The resin and hardener should retain its chemical properties for at least 12 months when stored between 68°F (20°C) and 95°F (35°C) in a dry place in its original closed packaging.

Contact Information:

North America:

U.S., Canada

& Mexico: 1-800-441-4369

Latin America:

Argentina: (+54) 11-4319-0100

Brazil: (+55) 11-5188-9000

Colombia: (+57) 1-219-6000

<http://www.poly-carb.com/>

Notice: No freedom from any patent or other intellectual property rights owned by Olin or others is to be inferred. Olin assumes no obligation or liability for the information in this document. The information provided herein is presented in good faith and is based on the best of Olin's knowledge, information, and belief. Since use conditions at non-Olin facilities are beyond Olin's control and government requirements may differ from one location to another and may change with time, it is solely the Buyer's responsibility to determine whether Olin's products are appropriate for the Buyer's use, and to assure the Buyer's workplace, use, and disposal practices are in compliance with applicable government requirements. Consequently, Olin assumes no obligation or liability for use of these materials and makes no warranty, express or implied. The user of the information provided is solely responsible for compliance with any applicable government requirements. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.